

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
15 January 2004 (15.01.2004)

PCT

(10) International Publication Number
WO 2004/005007 A1

(51) International Patent Classification⁷: **B29C 47/10**,
47/40 // C08J 5/00, B29K 21:00

(21) International Application Number:
PCT/EP2003/006928

(22) International Filing Date: 30 June 2003 (30.06.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
TO2002A000578 3 July 2002 (03.07.2002) IT

(71) Applicant (for all designated States except US): **FLLI
MARIS S.P.A.** [IT/IT]; Corso Moncenisio 22, I-10090
Rosta (IT).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **MARIS, Gianfranco**
[IT/IT]; Via Trento 23, I-10098 Rivoli (IT).

(74) Agents: **GERBINO, Angelo** et al.; Jacobacci & Partners
SpA, Corso Regio Parco 27, I-10152 Torino (IT).

(81) Designated States (national): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC,
SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA,
UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:


- as to applicant's entitlement to apply for and be granted
a patent (Rule 4.17(ii)) for the following designations AE,
AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA,
CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES,
FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH,
PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN,
TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO
patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG,
ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU,
TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE,
DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT,
RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)
- of inventorship (Rule 4.17(iv)) for US only

Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: A METHOD FOR THE CONTINUOUS PRODUCTION OF A COMPOSITION COMPRISING RUBBER, HYDRO-
CARBON RESIN AND SOLVENT



(57) Abstract: The method for the continuous production of a composition comprising rubber (20), hydrocarbon resin (22), and solvent (26) provides for the use of a dual-screw extruder (10), for example, a co-rotating dual-screw extruder. Preferably, at least a fraction of the solvent (26) is added at a point of the extruder (10) that is downstream of the initial section, for example, at a distance of at least 4 D from the initial section of the extruder (10).

BEST AVAILABLE COPY

A method for the continuous production of a composition comprising rubber, hydrocarbon resin and solvent

The present invention relates to a method for the production of a composition comprising rubber, hydrocarbon resin and solvent, in particular, an adhesive formulation.

According to the prior art, these compositions are produced in dissolving apparatus in which the various ingredients are added by a "batch" method and are left in contact until the solvent has dissolved the rubber and the hydrocarbon resin as well as any additives that are present. However, this method does not ensure uniformity of the properties of the various production batches of a given composition.

To prevent this problem, the subject of the present invention is a method for the continuous production of a composition of the type indicated above, with the use of a dual-screw extruder.

The use of a continuous production system ensures the reproducibility of the properties of the final composition over time. In fact, the control systems with which an extruder is typically provided ensure that the process parameters - such as, for example, the time spent in the extruder, the amount of energy supplied per unit of product, the number of revolutions of the screws per unit of time, the thermal profile, and the like - which influence these properties, are maintained over time.

Moreover, the use of a dual-screw extruder, preferably of the co-rotating type, enables effective mixing of the various components of the composition to be achieved, also allowing the solvent content of the composition to be reduced, typically from values of about 65% to values of

about 45-50%. This reduction is particularly significant in view of the fact that the recovery of the solvent from the final composition involves considerable costs and that a certain quantity of solvent - proportional to that which is present initially - is in any case dispersed to the exterior, resulting in environmental and economic damage.

The method of the invention preferably provides for the addition of at least one fraction of the solvent at a point of the extruder that is downstream of its initial section. Even more preferably, the solvent is added at a plurality of different points disposed downstream of the initial section of the extruder. For example, the first addition of solvent may take place at a distance of at least $4 D$ (where D denotes the diameter of one of the two extruder screws), for example, $20 D$, from the initial section of the extruder.

Advantageously, in the portion of the extruder that is upstream of the point at which the first addition of solvent is performed, the temperature is kept within a range of between 60°C and 120°C whereas, in the portion of the extruder that is downstream of the point at which the first addition of solvent is performed, the temperature is kept within a range of between 40°C and 80°C , the temperature in the upstream portion being greater than that prevailing in the downstream portion.

The rubber used may be selected from the group consisting of natural rubbers, synthetic rubbers, and mixtures thereof, for example, styrene-isoprene-styrene (SIS), styrene-butadiene-styrene (SBS), and natural rubber (NR).

As is known, a hydrocarbon resin is a resin prepared by the polymerization of unsaturated constituents of coal tar, rosin, or petroleum. Hydrocarbons having tackifying

properties, for example, of the type marketed under the name Escorez or Wing-tack, and mixtures thereof are preferably used.

The solvent is selected, for example, from the group consisting of hexane, pentane, dichloropropane, and mixtures thereof.

Further advantages and characteristics of the present invention will become clear from the following detailed description which is given with reference to the appended drawings, in which:

Figure 1 shows schematically a dual-screw extruder in which a method according to the invention is implemented, and

Figures 2 and 3 show schematically respective dual-screw extruders in which further embodiments of the method of the invention are implemented.

A method for the continuous production of a composition comprising rubber, hydrocarbon resin, and solvent provides for the use (Figure 1) of a dual-screw extruder 10, for example, of the co-rotating type.

A first section 12, a second section 14, a third section 16, and a fourth section 18, arranged in succession, are distinguished in the extruder 10. The first section 12 has a length equal to $16 D$ (where D denotes the diameter of one of the two screws of the extruder 10), the second section 14 has a length equal to about $12 D$, the third section 16 has a length equal to about $12 D$, and the fourth section 18 has a length equal to about $16 D$.

Rubber 20, hydrocarbon resin 22, as well as conventional additives 24, for example, oxidising agents, are introduced at the beginning of the first section 12. The temperature of the first section 12 is kept between 60 and 120°C. Homogenization of the ingredients introduced takes place in the first section 12.

A fraction of between 5 and 20% of the total solvent 26 is introduced at the beginning of the second section 14. The temperature of the second section 14 is kept between 30 and 80°C. Dissolving of the rest of the ingredients in the solvent 26 takes place in the second section 14.

A further fraction of between 5 and 20% of the total solvent 26 is introduced at the beginning of the third section 16. The temperature of the third section 16 is kept between 20 and 60°C. Further dissolving of the rest of the ingredients in the solvent 26 takes place in the third section 16.

Further fractions of the solvent 26 are introduced at the beginning of and along the fourth section 18, so as to reach the desired total quantity of solvent. The temperature of the fourth section 18 is kept between 20 and 40°C. Complete dissolving of the rest of the ingredients in the solvent 26 is achieved in the fourth section 18. The temperature of the composition produced at the outlet of the extruder 10 must necessarily be less than the boiling point of the solvent 26 used.

A variant of the production method of the invention is described with reference to Figure 2. In this variant, a first section 12, a second section 14, a third section 16, a fourth section 18, and a fifth section 28, arranged in succession, are distinguished in the extruder 10. The first section 12 has a length of about 12 D, the second section 14

has a length of about 8 D, the third section 16 has a length of about 12 D, the fourth section 18 has a length of about 8 D, and the fifth section 28 has a length of about 16 D.

Rubber 20, a fraction of between 30 and 50% of the total hydrocarbon resin 22, as well as additives 24, are introduced at the beginning of the first section 12. The temperature of the first section 12 is kept between 60 and 120°C. Homogenization of the ingredients introduced takes place in the first section 12.

The remaining fraction of the hydrocarbon resin 22 is introduced at the beginning of the second section 14. The temperature of the second section 14 is kept between 60 and 80°C. Further homogenization of the ingredients introduced takes place in the second section 14.

A fraction of between 5 and 20% of the total solvent 26 is introduced at the beginning of the third section 16. The temperature of the third section 16 is kept between 30 and 80°C. Dissolving of the rest of the ingredients in the solvent takes place in the third section 16.

A further fraction of between 5 and 20% of the total solvent 26 is introduced at the beginning of the fourth section 18. The temperature of the fourth section 18 is kept between 20 and 60°C. Further dissolving of the rest of the ingredients in the solvent takes place in the fourth section 18.

Further fractions of solvent 26 are introduced at the beginning of and along the fifth section 28 so as to reach the desired total quantity of solvent. The temperature of the fifth section 28 is kept between 20 and 40°C. Complete dissolving of the rest of the ingredients in the solvent 26 is achieved in the fifth section 28. The temperature of the

composition produced at the outlet of the extruder 10 must necessarily be less than the boiling point of the solvent 26 used.

A further variant of the production method of the invention is described with reference to Figure 3. In this variant, a first section 12, a second section 14, and a third section 16, arranged in succession, are distinguished in the extruder 10. The first section 12 has a length of about 20 D, the second section 14 has a length of about 12 D and the third section 16 has a length of about 24 D.

Rubber 20, hydrocarbon resin 22, and additives 24 are introduced at the beginning of the first section 12 and a fraction of between 2 and 10% of the total solvent 26 is introduced at a distance of 4 D from the beginning of the extruder 10. The temperature of the first section 12 is kept between 40 and 80°C. Homogenization of the ingredients introduced takes place in the first section 12.

A fraction of between 5 and 20% of the total solvent 26 is introduced at the beginning of the second section 14. The temperature of the second section 14 is kept between 30 and 60°C. Dissolving of the rest of the ingredients in the solvent 26 takes place in the second section 14.

Further fractions of solvent 26 are introduced at the beginning of and along the third section 16 so as to reach the desired total quantity of solvent. The temperature of the third section 16 is kept between 20 and 40°C. Complete dissolving of the rest of the ingredients in the solvent 26 is achieved in the third section 16. The temperature of the composition produced at the outlet of the extruder 10 must necessarily be less than the boiling point of the solvent 26 used.

Naturally, the principle of the invention remaining the same, the details of construction and forms of embodiment may vary widely with respect to those described purely by way of example, without thereby departing from its scope.

CLAIMS




1. A method for the continuous production of a composition comprising rubber (20), a hydrocarbon resin (22), and a solvent (26), with the use of a dual-screw extruder (10).
2. A method according to Claim 1, which provides for the addition of at least a fraction of the solvent (26) at a point of the extruder (10) that is downstream of the initial section.
3. A method according to Claim 2, in which a first addition of solvent (26) takes place at a distance of at least 4 D from the initial section of the extruder (10).
4. A method according to Claim 2 or Claim 3 in which the solvent (26) is added at a plurality of different points disposed downstream of the initial section of the extruder (10).
5. A method according to Claim 3 or Claim 4 in which, in the portion of the extruder (10) that is upstream of the point at which the first addition of solvent (26) is performed, the temperature is kept within a range of between 60°C and 120°C whereas, in the portion of the extruder (10) that is downstream of the point at which the first addition of solvent (26) is performed, the temperature is kept within a range of between 40°C and 80°C, the temperature in the upstream portion being greater than that prevailing in the downstream portion.
6. A method according to any one of the preceding claims, which provides for the addition of at least a fraction of the hydrocarbon resin (22) at a point of the extruder (10) that is downstream of the initial section.

7. A method according to any one of the preceding claims in which the rubber (20) is selected from the group consisting of natural rubbers, synthetic rubbers and mixtures thereof.

8. A method according to any one of the preceding claims in which the hydrocarbon resin (22) has tackifying properties.

9. A method according to any one of the preceding claims in which the solvent (26) is selected from the group consisting of hexane, pentane, dichloropropane, and mixtures thereof.

10. A method according to any one of the preceding claims in which the dual-screw extruder (10) is of the co-rotating type.



INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 03/06928

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B29C47/10 B29C47/40 C08J3/02 C09J5/00 //B29K21:00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B29C C08J C09J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 906 421 A (PLAMTHOTTAM SEBASTIAN S ET AL) 6 March 1990 (1990-03-06)	1,7-10
Y	column 11, paragraph 4 column 13, last paragraph; claim 1	2,4
Y	EP 0 774 481 A (TONEN SEKIYUKAGAKU KK) 21 May 1997 (1997-05-21) page 3, line 30; claims 7-9; figures 3-10	2,4
A	EP 0 531 607 A (BERSTORFF GMBH MASCH HERMANN) 17 March 1993 (1993-03-17) figure 1	3,5
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

15 October 2003

Date of mailing of the international search report

27/11/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Van Nieuwenhuize, O

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP 03/06928

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 010, no. 339 (C-385), 15 November 1986 (1986-11-15) & JP 61 143439 A (KURARAY CO LTD), 1 July 1986 (1986-07-01) abstract ---	1,2
A	DATABASE WPI Section Ch, Week 198940 Derwent Publications Ltd., London, GB; Class A18, AN 1989-291111 XP002257938 & JP 01 215880 A (MITSUBISHI OIL CO), 29 August 1989 (1989-08-29) abstract ---	1,7-10
A	US 4 028 302 A (TYNAN DANIEL GREGORY) 7 June 1977 (1977-06-07) claim 1 ---	1
A	US 3 978 013 A (LAKSHMANAN PALLAVOOR R) 31 August 1976 (1976-08-31) claim 1 ---	7
A	US 3 517 096 A (WOOD JOHN O ET AL) 23 June 1970 (1970-06-23) example 1 ---	1
A	PATENT ABSTRACTS OF JAPAN vol. 013, no. 562 (C-665), 13 December 1989 (1989-12-13) & JP 01 234424 A (KANEGAFUCHI CHEM IND CO LTD), 19 September 1989 (1989-09-19) abstract ---	1
A	DE 32 12 643 A (CONTINENTAL GUMMI WERKE AG) 13 October 1983 (1983-10-13) claim 1 ---	1
A	US 4 431 598 A (KORPMAN RALF) 14 February 1984 (1984-02-14) claim 1 -----	7,8

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 03/06928

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4906421	A	06-03-1990	AU 2081688 A	30-01-1989
			AU 622414 B2	09-04-1992
			AU 631242 B2	19-11-1992
			AU 6199990 A	29-11-1990
			BR 8807118 A	17-10-1989
			CN 1030438 A	18-01-1989
			CN 1063707 A	19-08-1992
			DK 94789 A	18-04-1989
			EP 0329727 A1	30-08-1989
			ES 2010762 A6	01-12-1989
			JP 2500527 T	22-02-1990
			WO 8900106 A1	12-01-1989
			US 5100728 A	31-03-1992
			US 5180635 A	19-01-1993
EP 0774481	A	21-05-1997	JP 8245799 A	24-09-1996
			DE 69622665 D1	05-09-2002
			DE 69622665 T2	03-04-2003
			EP 0774481 A1	21-05-1997
			US 5741848 A	21-04-1998
			CA 2189868 A1	12-09-1996
			WO 9627631 A1	12-09-1996
EP 0531607	A	17-03-1993	DE 4130314 C1	15-10-1992
			DE 59203746 D1	26-10-1995
			EP 0531607 A2	17-03-1993
			JP 3217481 B2	09-10-2001
			JP 5200738 A	10-08-1993
			RU 2077422 C1	20-04-1997
			US 5262111 A	16-11-1993
JP 61143439	A	01-07-1986	NONE	
JP 1215880	A	29-08-1989	JP 2043622 C	09-04-1996
			JP 7068503 B	26-07-1995
US 4028302	A	07-06-1977	DE 2645318 A1	14-04-1977
			JP 52047044 A	14-04-1977
US 3978013	A	31-08-1976	NONE	
US 3517096	A	23-06-1970	DE 1669389 B1	27-04-1972
			FR 1536608 A	16-08-1968
			GB 1175192 A	23-12-1969
JP 01234424	A	19-09-1989	NONE	
DE 3212643	A	13-10-1983	DE 3212643 A1	13-10-1983
US 4431598	A	14-02-1984	NONE	

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.